

PEN / F BEIG

Argila micronitzada

Arcilla micronizada

Argile micronisée

Micronized clay



CARACTERÍSTIQUES FISIO-MECÀNQUES

Características / Caractéristiques / Characteristics

PÈRDUA AL FOC	Perdida al fuego	Perte au feu	Loss on ignition	8,50%
COLOR CRU	Color crudo	Couleur brute	Ecreu color	

ANÀLISI QUÍMIC

Análisi químico / Analyse chimique / Chemical analysis

Na2O	0,34%	Malla	%
MgO	2,52%	125	6,13%
Al2O3	18,13%	90	6,81%
SiO2	55,22%	63	9,71%
P2O3	0,14%	45	13,53%
K2O	3,59%	36	36,02%
CaO	4,62%	0	27,01%
TiO2	0,75%		
Fe2O3	6,20%		

GRANULOMETRIA

Granulometría / Taille du grain / Grain size

ANÀLISI RACIONAL

Análisis racional / Analyse rationnelle / Rational analysis

Montmorillonita	Montmorillonita	Montmorillonite	Montmorillonite	3,00%
Clorita	Clorita	Chlorite	Chlorite	2,00%
Illita	Illita	Illite	Illite	2,40%
Caolinita	Caolinita	Kaolinite	Kaolinite	9,00%
Quars	Cuarzo	Quartz	Kaolinite	43,00%
Feldespat potàssic	Feldespat potàssic	Feldspath potassique	Potassium feldspar	4,00%
Plagioclasa	Plagioclasa	Plagioclase	Plagioclase	5,00%
Hematita	Hematita	Hématite	Hematite	3,00%
Calcita	Calcita	Calcite	Calcite	7,00%
Dolomita	Dolomita	Dolomie	Dolomite	3,00%