

M-2 2mm

Argila

Arcilla

Argile

Clay



CARACTERÍSTIQUES FISIO-MECÀNIQUES

Características / Caractéristiques / Characteristics

PÈRDUA AL FOC	Perdida al fuego	Perte au feu	Loss on ignition	8,50%
COLOR CRU	Color crudo	Couleur brute	Ecru color	

ANÀLISI QUÍMIC

Análisi químico / Analyse chimique / Chemical analysis

Na ₂ O	0,34%
MgO	2,52%
Al ₂ O ₃	18,13%
SiO ₂	55,22%
P ₂ O ₃	0,14%
K ₂ O	3,59%
CaO	4,62%
TiO ₂	0,75%
Fe ₂ O ₃	6,20%

ANÀLISI RACIONAL

Análisis racional / Analyse rationnelle / Rational analysis

Montmorillonita	Montmorillonita	Montmorillonite	Montmorillonite	3,00%
Clorita	Clorita	Chlorite	Chlorite	2,00%
Illita	Illita	Illite	Illite	2,40%
Caolinita	Caolinita	Kaolinite	Kaolinite	9,00%
Quars	Cuarzo	Quartz	Kaolinite	43,00%
Feldespat potàssic	Feldespato potásico	Feldspath potassique	Potassium feldspar	4,00%
Plagioclasa	Plagioclasa	Plagioclase	Plagioclase	5,00%
Hematita	Hematita	Hématite	Hematite	3,00%
Calcita	Calcita	Calcite	Calcite	7,00%
Dolomita	Dolomita	Dolomie	Dolomite	1,00%